

Product Type:	Bi-directional Filament Tape														
Colour:	Translucent														
Roll Size:	Widths 6mm to 1,060mm in 45m Lengths (Longer lengths, MOQs apply)														
Adhesive:	Rubber Synthetic														
Description:	A Polypropylene Film laminated to Cross Mesh of Fibreglass Strands for Reinforcement coated with a Synthetic Rubber Adhesive system.														
Application:	General Strapping & bundling jobs and heavy duty carton sealing, Spine binding and reinforcement. Holding concrete shuttering in place.														
Technical Details:	<table><tr><td>Gauge:</td><td>0.14mm</td></tr><tr><td>Adhesion to Steel:</td><td>7.2 N/cm</td></tr><tr><td>Rolling Ball Tack:</td><td>10#</td></tr><tr><td>Tensile Strength:</td><td>320 N/cm</td></tr><tr><td>Elongation at Break:</td><td>12%</td></tr><tr><td>Service Temperature:</td><td>0°C to 60°C</td></tr><tr><td>Storage Temperature:</td><td>15°C to 25°C</td></tr></table>	Gauge:	0.14mm	Adhesion to Steel:	7.2 N/cm	Rolling Ball Tack:	10#	Tensile Strength:	320 N/cm	Elongation at Break:	12%	Service Temperature:	0°C to 60°C	Storage Temperature:	15°C to 25°C
Gauge:	0.14mm														
Adhesion to Steel:	7.2 N/cm														
Rolling Ball Tack:	10#														
Tensile Strength:	320 N/cm														
Elongation at Break:	12%														
Service Temperature:	0°C to 60°C														
Storage Temperature:	15°C to 25°C														
Surface Preparation:	The surface on which the tape is to be used must be clean, dry and free from grease and dust. Remember that pressure sensitive adhesive must be applied with the maximum possible pressure in order to achieve maximum adhesion levels. The recommended application temperature is between 15°C and 25°C.														
Storage:	Tapes stored below the minimum application temperature will require warming up to that level before use. Up to 24 hours may be required for this to take place.														



DISCLAIMER:

Values: All values presented have been determined by standard test methods and are average values only.

Recommendations: Whilst we are happy to recommend products from our range for applications, it is imperative that the customer/user complete their own tests to determine suitability for their application under "working conditions" and if longevity is important, that ageing tests be carried out.

Warranty: We can only warranty our products to the level that they are consistent with our Product Information Sheet values

BUT CANNOT accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.